

# DUPLISOLE 24

A-Silicone Duplicating Material



## DUPLISOLE 24

Duplicating material used in dental laboratories.

### ADVANTAGES


- Extreme accuracy of detail reproduction
- Good elasticity and tear resistance
- Easy to dose and mix
- Unaltered in time even after weeks
- Compatible with plasters, investments and resins
- Fast Setting

### CHARACTERISTICS

- Mixing ratio 1:1
- High fluidity
- Low final hardness
- Resistant to high temperature
- Long dimensional stability
- Light blue color

Piece by Piece  
with *pleasure.*

Premium Plus Japan commitment  
to the own manufacture products



### TECHNICAL DATA

#### Duplisolet 24

Mixing time	1'
Total working time (23°C)	5'
Setting time (23°C)	20'
Hardness after 24 hours	24 Shore A
Linear dimensional change	< 0,05%

### PACKAGING

PJ9990	Duplisolet 24 1+1Kg
PJ9990-S	Duplisolet 24 250+250g

### MAIN APPLICATION

Duplication of models in fixed  
and removable prostheses.

Available by the authorized dealer

# SOLE A-LAB PUTTY 85

A-Silicone Matrix Material - Hard Type



## SOLE A-LAB PUTTY 85

Putty consistency addition silicone used in dental laboratories.



### ADVANTAGES


- Good reproduction of detail
- Hard after polymerization
- Easy to dose and mix
- Stable and accurate during repositioning
- Unaltered in time even after weeks
- Compatible with CAD/CAM scanners

### CHARACTERISTICS

- Mixing ratio 1:1
- Biocompatible
- High final hardness
- Resistant to high temperature
- Long dimensional stability
- Light green color

Piece by Piece  
with *pleasure.*

Premium Plus Japan commitment to the own manufacture products



### TECHNICAL DATA Sole A-Lab Putty 85

Mixing time	30"
Total working time (23°C)	2'
Setting time (23°C)	6'
Hardness after 24 hours	85 Shore A
Linear dimensional change	< 0,2%
Elastic recovery	> 99,5%

### PACKAGING

PJ9960	Sole A-Lab Putty 85 1.5 + 1.5Kg
PJ9960-S	Sole A-Lab Putty 85 400 + 400g

### MAIN APPLICATION

- Matrix for temporary crowns/bridges
- Matrix for partial/full denture with cold resin
- Bite registration key on the articulator
- Matrix for designing metal structures
- Matrix for verticulator techniques
- Isolation of full denture/teeth in the flask

Available by the authorized dealer

# SOLE A-LAB PUTTY 95

A-Silicone Matrix Material - Extra Hard Type



## SOLE A-LAB PUTTY 95

Putty consistency addition silicone used in dental laboratories.

### ADVANTAGES

- Extremely hard after polymerization
- Easy to dose and mix
- Stable and accurate during repositioning
- Unaltered in time even after weeks
- Compatible with CAD/CAM scanners

### CHARACTERISTICS

- Mixing ratio 1:1
- Biocompatible
- Very high final hardness
- Resistant to high temperature
- Long dimensional stability
- Light blue color



Piece by Piece  
with *pleasure.*

Premium Plus Japan commitment to the own manufacture products



### TECHNICAL DATA Sole A-Lab Putty 95

Mixing time	30"
Total working time (23°C)	2'
Setting time (23°C)	6'
Hardness after 24 hours	95 Shore A
Linear dimensional change	< 0,2%
Elastic recovery	> 99,5%

### PACKAGING

PJ9970	Sole A-Lab Putty 95 1.5 + 1.5Kg
PJ9970-S	Sole A-Lab Putty 95 400 + 400g

### MAIN APPLICATION

- Matrix for temporary crowns/bridges
- Matrix for partial/full denture with cold resin
- Bite registration key on the articulator
- Matrix for designing metal structures
- Matrix for verticulator techniques
- Isolation of full denture/teeth in the flask

Available by the authorized dealer

# SOLE C-LAB PUTTY 85

C-Silicone Matrix Material



## SOLE C-LAB PUTTY 85

Putty consistency condensation silicone  
used in dental laboratories.

### ADVANTAGES

- Very smooth surface after polymerization
- Soft and moldable consistency
- Stable and accurate in repositioning
- Accurate in detecting details
- Hard-85 Sh-A final hardness
- Resistant in hot water
- It can be mixed with any type of gloves

### CHARACTERISTICS

- High final hardness
- Soft and easy to work
- Precise dosage
- Flexible mixing time
- Not pigmented
- To be mixed with Solegel Catalyst



Piece by Piece  
with *pleasure.*

Premium Plus Japan commitment  
to the own manufacture products



### TECHNICAL DATA Sole C-Lab Putty 85

Mixing time	30"
Total working time (23°C)	1'30"
Setting time (23°C)	5'30"
Hardness after 24 hours	85 Shore A
Linear dimensional change	< 0,2%
Elastic recovery	> 99%

### PACKAGING

PJ9900-S	Sole C-Lab Putty 85 1.5 Kg + Gel
PJ9900	Sole C-Lab Putty 85 5 Kg
PJ9910	Sole C-Lab Putty 85 5 Kg + 2 Gel
PJ9920	Sole C-Lab Putty 85 2,6kg
PJ9930	Sole C-Lab Putty 85 10Kg + 4 Gel
PJ9950	Solegel 60g

### MAIN APPLICATION

Matrix for temporary crowns/bridges  
Matrix for partial denture with cold resin  
Matrix for gingival mask on the model  
Bases for denture repair  
Isolation of full denture/teeth in the flask

Available by the authorized dealer



# SOLEBITE S

## Extra Hard

Bite Registration addition silicone (VPS)





## SOLEBITE S

Extra Hard

**Bite registration addition silicone (VPS)  
used in dental clinic and laboratory.**

### ADVANTAGES

- Very high final hardness
- Easy to be injected on the teeth
- Low bite resistance from the patient
- Quick polymerization
- Easy to see occlusal contact point
- Long dimensional stability
- Easy to trim

### CHARACTERISTICS

- Extra Hard (95 Sh-A)
- Fast Setting
- Biocompatible
- Thixotropic
- 3 years shelf-life
- Dark blue color



### TECHNICAL DATA SoleBite S Extra Hard

Total working time (23°C)	20"
Time in mouth	30"
Setting time (23°C)	50"
Hardness after 24 hours	>95 Shore A
Linear dimensional change	< 0,13%
Detail reproduction	<20 μm

### PACKAGING

PJ8190-Ex	Solebite S EH 50mlx2 + mixers
PJ8190B-Ex	Solebite S EH 50mlx4 eco
PJ8190-1-Ex	Sample Solebite S EH 50ml
DC-0123	Mixing tips green 50pcs
DEL5025	Bite Tips Eco 50pcs
PJ8010	Dispenser PJ

### MAIN APPLICATION

Occlusal or vestibular bite registration keys of partial / full arch.

Available by the authorized dealer

# SOLEBITE S

Bite Registration addition silicone (VPS)



## SOLEBITE S

Bite registration addition silicone (VPS)  
used in dental clinic and laboratory.

### ADVANTAGES

- Easy to be injected on the teeth
- Low bite resistance from the patient
- Quick polymerization
- High final hardness
- Easy to see occlusal contact point
- Long dimensional stability
- Easy to trim

### CHARACTERISTICS

- Hard (90 Sh-A)
- Fast Setting
- Biocompatible
- Thixotropic
- 3 years shelf-life
- Light blue color



### TECHNICAL DATA

#### SoleBite S

Total working time (23°C)	20"
Time in mouth	30"
Total setting time (23°C)	50"
Hardness after 24 hours	90 Shore A
Linear dimensional change	< 0,13%
Detail reproduction	<20 μm

### PACKAGING

PJ8110-Ex	Solebite S 50mlx2 + mixers
PJ8110-Ex	Sample Solebite S 50ml
DC-0123	Mixing tips green long 50pcs
DEL5025	Bite Tips Eco 50pcs
PJ8010	Dispenser PJ

### MAIN APPLICATION

Occlusal or vestibular bite registration keys of partial / full arch.

Available by the authorized dealer

# SOLEBITE S

## Super Fast

Bite Registration addition silicone (VPS)



## SOLEBITE S Super Fast

**Bite registration addition silicone (VPS)  
used in dental clinic and laboratory.**

### ADVANTAGES

- Extra fast polymerization
- Low residual of silicone into the mixer (short version)
- Easy to be injected on the teeth
- Low bite resistance from the patient
- High final hardness
- Easy to see occlusal contact point
- Long dimensional stability
- Easy to trim

### CHARACTERISTICS

- Extra Fast Setting
- Hard (90 Sh-A)
- Biocompatible
- Thixotropic
- 3 years shelf-life
- Indigo blue color



### TECHNICAL DATA SoleBite S Super Fast

Total working time (23°C)	15"
Time in mouth	20"
Total setting time (23°C)	35"
Hardness after 24 hours	90 Shore A
Linear dimensional change	< 0,13%
Detail reproduction	<20 μm

### PACKAGING

PJ8180-Ex	Solebite S SF 50mlx2 + mixers
PJ8180-Ex	Sample Solebite S SF 50ml
DC-0127	Mixing tips green short 50pcs
DEL5025	Bite Tips Eco 50pcs
PJ8010	Dispenser PJ

### MAIN APPLICATION

Occlusal or vestibular bite registration keys of partial / full arch.

Available by the authorized dealer

## SOLEGEL


Catalyst Gel for C-Silicone used in dental laboratories.

### ADVANTAGES

- Accurate dosing through calibrated tip
- Easy to be mixed

### CHARACTERISTICS

- Gel consistency
- Homogeneous formulation
- Mixed with Sole C-Lab Putty 85
- Red color



### MAIN APPLICATION

Used to polymerize Sole C-Lab Putty 85

### TECHNICAL DATA Solegel with C-Lab 85

Mixing time	30"
Total working time (23°C)	1'30"
Setting time (23°C)	5'30"
Hardness after 24 hours	85 Shore A
Linear dimensional change	< 0,2%
Elastic recovery	> 99%

### PACKAGING

PJ9950 Solegel 60g