

SOLE C-LAB PUTTY 85

C-Silicone Matrix Material



SOLE C-LAB PUTTY 85

Putty consistency condensation silicone
used in dental laboratories.

ADVANTAGES

- Very smooth surface after polymerization
- Soft and moldable consistency
- Stable and accurate in repositioning
- Accurate in detecting details
- Hard-85 Sh-A final hardness
- Resistant in hot water
- It can be mixed with any type of gloves

CHARACTERISTICS

- High final hardness
- Soft and easy to work
- Precise dosage
- Flexible mixing time
- Not pigmented
- To be mixed with Solegel Catalyst



Piece by Piece
with *pleasure.*

Premium Plus Japan commitment
to the own manufacture products



TECHNICAL DATA Sole C-Lab Putty 85

Mixing time	30"
Total working time (23°C)	1'30"
Setting time (23°C)	5'30"
Hardness after 24 hours	85 Shore A
Linear dimensional change	< 0,2%
Elastic recovery	> 99%

PACKAGING

PJ9900-S	Sole C-Lab Putty 85 1.5 Kg + Gel
PJ9900	Sole C-Lab Putty 85 5 Kg
PJ9910	Sole C-Lab Putty 85 5 Kg + 2 Gel
PJ9920	Sole C-Lab Putty 85 2,6kg
PJ9930	Sole C-Lab Putty 85 10Kg + 4 Gel
PJ9950	Solegel 60g

MAIN APPLICATION

Matrix for temporary crowns/bridges
Matrix for partial denture with cold resin
Matrix for gingival mask on the model
Bases for denture repair
Isolation of full denture/teeth in the flask

Available by the authorized dealer