

SOLE A-LAB PUTTY 85

A-Silicone Matrix Material - Hard Type



SOLE A-LAB PUTTY 85

Putty consistency addition silicone used in dental laboratories.

ADVANTAGES

- Good reproduction of detail
- Hard after polymerization
- Easy to dose and mix
- Stable and accurate during repositioning
- Unaltered in time even after weeks
- Compatible with CAD/CAM scanners

CHARACTERISTICS

- Mixing ratio 1:1
- Biocompatible
- High final hardness
- Resistant to high temperature
- Long dimensional stability
- Light green color

Piece by Piece
with *pleasure.*

Premium Plus Japan commitment to the own manufacture products



TECHNICAL DATA Sole A-Lab Putty 85

Mixing time	30"
Total working time (23°C)	2'
Setting time (23°C)	6'
Hardness after 24 hours	85 Shore A
Linear dimensional change	< 0,2%
Elastic recovery	> 99,5%

PACKAGING

PJ9960	Sole A-Lab Putty 85 1.5 + 1,5Kg
PJ9960-S	Sole A-Lab Putty 85 400 + 400g
PJ9965	Sole A-Lab Putty 85 5+5Kg

MAIN APPLICATION

- Matrix for temporary crowns/bridges
- Matrix for partial/full denture with cold resin
- Bite registration key on the articulator
- Matrix for designing metal structures
- Matrix for verticulator techniques
- Isolation of full denture/teeth in the flask

Available by the authorized dealer